

PHTHALIC ANHYDRIDE	
PHYSICAL APPEARANCE	SNOW WHITE FREE FLOWING FLAKES
COLOR OF MOLTEN MATERIAL (APHA)	20 MAX.
COLOR OF MOLTEN MATERIAL AT 250 °C FOR 90mts. (APHA)	60 MAX.
SOLIDIFICATION POINT	130.80 °C MIN.
PURITY AS C ₈ H ₄ O ₃	99.80% MIN.
MALEIC ANHYDRIDE & OTHER OXIDISABLE IMPURITIES EXPRESSED AS C ₈ H ₄ O ₃	0.050 MAX.