

Chlorinated Paraffin Wax (CPW) 70% Powder	
CL CONTENT	69-73%
MOISTURE	0.5% MAX.
FE CONTENT	0.005% MAX.
ACID VALUE	0.5 mgKOH/g max.
SOFTENING POINT	90-103 deg C
MESH	95% through 40 mesh min.
THERMAL DECOMPOSITION TEMP.	175 Deg C MIN.
HEAT STABILITY INDEX	0.05% MAX.
COLOUR	250 APHA MAX.
VOLATILE MATTER	0.1% MAX.
CARBON TETRACHLORIDE CONTENT	50 PPM MAX.
DENSITY	1.6 X 103Kg / M3